



# TECHNICAL DATA SHEET

## 2K Eco Varnish 1900



### Description

2K Clear economical Polyurethane Varnish used for both wood and vehicles. It provides a glossy finish and has good film appearance.

**For application:** Set used with EGC Hardener & Thinner.

### Product preparation - Application



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Surfaces must be dried / flashed-off in accordance with TDS before application.  
Existing finishes: Surfaces must be sanded and degreased before application using EGC Cleaning Thinner no.111.



Mixing Ratio	Volume
<b>Clear 1900</b>	<b>100</b>
<b>Hardener 1806</b>	<b>50</b>
<b>Thinner (1807W - 1812S) or Global Thinner</b>	<b>50</b>




16:22 sec / (cup ford 4).



Pot Life: 3-4 hr at 23°C.



	Spray Nozzle	Spray Pressure
<b>Conventional</b>	<b>1:3 - 1.5 mm</b>	<b>3.0 – 4.0 bars</b>



2 coats  
intermediate and final flash-off: 5 min.



Air Dry	Baking Time
<b>12 hr./ 23°C</b>	<b>30 min/ 80°C or 45 min/ 60°C</b>



Infrared (Short wave): 5-10 min.



# TECHNICAL DATA SHEET

## 2K Eco Varnish 1900

---

**Shelf life:** 2 years in good storing conditions (25°C, 65% humidity).

### Remarks

- Ensure there is maximum ventilation during application.
- Wear the safety glasses and gloves.
- Keep out of reach of children.

---

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our product range.

The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.