



# TECHNICAL DATA SHEET



## NC Primer Surfacer







### Description:

A quick air drying Nitrocellulose, Alkyd Primer Surfacer designed for metal and wood substrates. The product has excellent filling, sanding and water resistance properties in addition to its protective value.

### Features:

The product can be used either as a Primer Surfacer or a Filler that is applied in two or three spray coats.

### Product preparation - Application

	It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.
	Clean with Thinner 111 or 111J or any suitable cleaning Thinner. Sand with P80-P120 (Galvanized steel and old paintwork with P240).
	After dilution with the recommended Thinner, apply number of spray coats 2 - 3 by using spray gun (nozzle diameter 1.6 - 1.8 mm, air pressure 3.5 - 4.5 bar) to give a smooth film of average dry film thickness 30 - 60 µm.
	23°C for 15-20 min.
	Infrared (short wave): IR equipment Half power: 5 – 7 min.
	Sanding manual, P400-800. Sanding manual, or P600 soft pad.

**Shelf life:** 2 years in good storing conditions (23 ± 2°C 50 ± 5 % humidity). Keep away from direct sunlight.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our product range.

The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.