



TECHNICAL DATA SHEET

AUTO PRO - 706 2K Undercoat



Description:

2K Undercoat 706 is texture thixotropic paint, paintable and chip-resistant for the car underneath and wheel house. It offers a long-term solution for issues related to corrosion and rust, also minimizes sound from underneath the vehicle and insulates against the heat and cold, increasing the longevity of the car.

Product preparation - Application



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



EGC 2K undercoat 706 should be applied over rust free and degreased bare metal. For longer resistance to corrosion.



Mixing Ratio	Weight
Hardener - H100	5:1



Use undercoat 706
Nozzle: 6-8 mm; Pressure:4-5 bar
Apply 1-2 coats.



Oven	Air Dry
60 °C 45 min. - 80 °C 30 min.	10-12 hr.

Shelf life: 1 year in good storing conditions (23 ± 2°C 50 ± 5 % humidity). Keep away from direct sunlight.

Remarks

- Ensure there is maximum ventilation during application.
- Wear the safety glasses and gloves.
- Keep out of reach of children.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our product range.

The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.