



TECHNICAL DATA SHEET

BONDU

Nitro Alkyd Air Dry Topcoat - All colors



Description:

One component nitro alkyd lacquer that has been developed for the field of automotive repair. It dries quickly, easy to apply, weathering resistance and has good hardness and polish capability.

Product preparation - Application



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.




Old or original paintwork well sanded and cleaned. Primer-Surfacers or Surfacers, sanded and cleaned. Surfaces must be prepared and cleaned correctly before application. Repair areas should be sanded with P500-P600 (by machine) or P800-P1000 (by hand) then cleaned using EGC cleaning thinner 111.



16:20 sec / (cup ford 4) using EGC Global Thinner or any suitable Thinner.



	Spray nozzle	Spray pressure
Conventional	1.4 - 1.6 mm	3 - 5 bar

**Number of coats:**

Apply 2 - 3 single coats with flash off time 3 - 5 min. between coats.
Total dry film thickness 30 - 40 microns.



Dry to Touch	Dry to Handle
15 - 20 min	24 hr.

Shelf life: 2 years in good storing conditions (23 ± 2°C 50 ± 5 % humidity). Keep away from direct sunlight.

Remarks

- Ensure there is maximum ventilation during application.
- Wear the safety glasses and gloves.
- Keep out of reach of children.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our product range.

The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.